



HIGH PURITY INSULATING CASTABLE

PRODUCT: ACCGUN INS 8
TYPE: INSULATING GUNNING MATERIAL
NATURE OF BOND: HYDRAULIC
INSTALLATION: GUNNING

GENERAL PROPERTIES

MAX. SERVICE TEMPERATURE: 900 °C
MAXIMUM GRAIN SIZE: 6 mm
WATER REQUIRED FOR CASTING: 42 – 48 %

CHEMICAL ANALYSIS, %

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Fe ₂ O ₃	5.00 – 6.00	5.30	BIS 12107 Part 6

PHYSICAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Dry density, g / cc after drying at 110 °C / 24 hrs	0.70 – 0.85	0.78	BIS 10570
CCS, kg/cm ² after drying at 110 °C / 24 hrs after heating at 800 °C / 3 hrs	20 – 40 15 – 30	25 20	BIS 10570 BIS 10570
MOR, kg/cm ² after drying at 110 °C / 24 hrs after heating at 800 °C / 3 hrs	8 – 15 6 – 12	10 8	BIS 10570 BIS 10570
% Retained on maximum size	0 – 5	1.4	BIS 1528 Part 14

THERMAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Refractoriness, Orton / °C		+ 12 / + 1337	BIS 1528 Part 1
PLC, % after heating at 800 °C / 3 hrs	(- 1.00) to (+ 1.00)	- 0.56	BIS 10570
Thermal Conductivity, kcal/m/hr/°C at 500 °C HF	0.18 – 0.23	0.21	WATER CALORIMETRIC METHOD

Packaging: 25 kg bags

Delivery State: Dry

Storage Life: Best till 9 months from the date of production, if stored in proper condition.

Note:

(1) The data are current production averages. They can not be used as limits for specification.

AUTH. CHANNEL PARTNER - VARSHA REFRACTORIES PVT. LTD.

Address : 04, Kailash Appt. R P Road, Near D Mart, Old RTO Compound, Behind Gurudev Hotel, Kalyan (W) 421301 Tel : 0251-2314832 / 2318832 Fax : 2314831

Email : refractory9@gmail.com Website : www.varsharefractories.com