



MEDIUM PURITY INSULATING CASTABLE

PRODUCT: INSULYTE 15
TYPE: MODERATE DENSITY INSULATING CASTABLE
NATURE OF BOND: HYDRAULIC
INSTALLATION: TAMPING

GENERAL PROPERTIES

MAX. SERVICE TEMPERATURE: 1350 °C
MAXIMUM GRAIN SIZE: 6 mm
WATER REQUIRED FOR CASTING: 24 – 29 %

CHEMICAL ANALYSIS, %

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Fe ₂ O ₃	2.7 – 3.2	3.10	BIS 12107 Part 6

PHYSICAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Dry density, g / cc after drying at 110 °C / 24 hrs	1.50 – 1.65	1.60	BIS 10570
CCS, kg/cm ² after drying at 110 °C / 24 hrs	95 – 110	100	BIS 10570
after heating at 1100 °C / 3 hrs	60 – 80	65	BIS 10570
after heating at 1300 °C / 3 hrs	70 – 90	78	BIS 10570
% Retained on maximum size	0 – 5	1.2	BIS 1528 Part 14

THERMAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Refractoriness, Orton / °C		15 / 1430	BIS 1528 Part 1
PLC, % after heating at 1100 °C / 3 hrs	(- 0.30) to (+0.30)	-0.12	BIS 10570
after heating at 1300 °C / 3 hrs	(- 1.00) to (+1.00)	+0.85	BIS 10570
Thermal Conductivity, kcal/m/hr/°C at 500 °C HF	0.42 – 0.47	0.445	WATER CALORIMETRIC METHOD

Packaging: 25 kg bags

Delivery State: Dry

Storage Life: Best till 9 months from the date of production, if stored in proper condition.

Note:

(1) The data are current production averages. They can not be used as limits for specification.

AUTH. CHANNEL PARTNER - VARSHA REFRACTORIES PVT. LTD.

Address : 04, Kailash Appt. R P Road, Near D Mart, Old RTO Compound, Behind Gurudev Hotel, Kalyan (W) 421301 Tel : 0251-2314832 / 2318832 Fax : 2314831

Email : refractory9@gmail.com Website : www.varsharefractories.com