



VARSHA
REFRACTORIES PVT. LTD.



REFRACTORY MORTAR

PRODUCT: ACCOSET 50 N
TYPE: 50 % ALUMINA MORTAR (COARSE)
NATURE OF BOND: CHEMICAL / CERAMIC

GENERAL PROPERTIES

Maximum Service Temperature: 1500 °C
Sintering Temperature: 1100 °C
Maximum Grain Size: 1.5 mm
Water for Trowelling Consistency : 20 – 28 %

CHEMICAL ANALYSIS, %

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Al ₂ O ₃	45.0 – 50.0	47.3	BIS 12107 Part 3
Fe ₂ O ₃	3.8 – 4.8	4.4	BIS 12107 Part 6

PHYSICAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
% Retained Above Maximum Size	1 – 5	1.50	BIS 1528 Part 14

THERMAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Pyrometric Cone Equivalent, Orton / °C	---	29 / 1659	BIS 1528 Part 1

Packaging: 50 Kg Bags **Storage Life:** 12 Months **Delivery State:** Dry

AUTH. CHANNEL PARTNER - VARSHA REFRATORIES PVT. LTD.

Address : 04, Kailash Appt. R P Road, Near D Mart, Old RTO Compound, Behind Gurudev Hotel, Kalyan (W) 421301 **Tel :** 0251-2314832 / 2318832 **Fax :** 2314831

Email : refractory9@gmail.com **Website :** www.varsharefractories.com